

COLORAMA 2 MULTICOLOUR

- Exclusive Colorama Trevira CS fabric woven with a multicolour yarn for texture and tonality
- Cradle to Cradle Certified™ Bronze
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 72°
- Proven acoustic properties

ANVENDELSER



ANGIVELSER OM VÆVNING

	Semitransparent
	Polyester Trevira CS
	260 g/m ²
	0.55 mm
	325 cm
	330 cm
	330 cm

VASKEANVISNINGER

							
	-1%	-2%	-2.5%	-0.5%			
							
	-1%						
							

TEKNISKE EGENSKABER

	6
	Alpha-w = 0.30 / 0.65
	Flammehæmmende
	Kan anvendes i fugtige områder
	Kun krydsbehandling
	Kun krydsbehandling
	Oeko-Tex, Cradle to Cradle

FLAMMEHÆMMENDE

B-s1,d0 (EN 13501-1)
 Class 1 (EN 13773)
 Class 1 (UNI 8456)
 B1 (DIN 4102-1)
 M1 (NF P 92-503/5/7)
 Type C (BS 5867-2)
 NFPA 701



Colorama 2 Multicolour

OPTISKE KOEFFICIENTER OG SOLKOEFFICIENTER ($\pm 5\%$, DIN EN 410)

Farve	T_V	T_S	R_S	A_S	T_{UV}	F_C	g_{tot}
111	27.4	27.0	64.4	8.6	6.6	0.53	0.38
131	17.8	18.9	47.6	33.5	6.8	0.63	0.45
161	12.6	13.3	39.1	47.6	5.1	0.68	0.49
181	8.4	8.7	27.8	63.5	4.0	0.75	0.54
211	24.9	26.4	59.4	14.2	8.0	0.56	0.40
261	12.6	13.1	37.9	49.0	5.1	0.69	0.49
431	12.3	18.2	46.3	35.5	5.0	0.64	0.46
461	9.8	17.3	43.8	38.9	4.8	0.65	0.47

T_V Visible light transmission

R_S Solar reflectance

T_{UV} UV transmission

g_{tot} Total g-value


T_S Solar transmission

A_S Solar absorption

F_C Shading factor

$F_C + g_{tot}$: Værdi beregnet med glas: $0.72 / U_g = 1.6 \text{ W/m}^2 \text{ K}$, DIN EN 13363-1


Colorama 2 Multicolour




111




131



161



181



211



261



431



461

De viste farver er ikke bindende