

COLORAMA ACOUSTIC MULTICOLOUR

- Exclusive Colorama Trevira CS fabric woven with acoustic and multicolour yarns for texture and tonality
- Superior acoustic properties which belie its agile appearance
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 60°

ANVENDELSER



ANGIVELSER OM VÆVNING

	Transparent
	92% Polyester Trevira CS, 8% Polyester
	140 g/m ²
	0.40 mm
	325 cm
	330 cm
	330 cm

VASKEANVISNINGER

						
	-1%	-2%	-0.5%			
						
	-1%					
						

TEKNISKE EGENSKABER

	6
	Alpha-w = 0.45 / 0.65
	Flammehæmmende
	Kan anvendes i fugtige områder
	Egnet til Wave
	Oeko-Tex

FLAMMEHÆMMENDE

Class 1 (EN 13773)
B1 (DIN 4102-1)
M1 (NF P 92-503/5/7)
Type B (BS 5867-2)



Colorama Acoustic Multicolour

OPTISKE KOEFFICIENTER OG SOLKOEFFICIENTER ($\pm 5\%$, DIN EN 410)

Farve	T_V	T_s	R_s	A_s	T_{UV}	F_C	g_{tot}
111	44.1	43.5	51.6	4.9	15.3	0.62	0.45
131	37.8	38.2	42.0	19.8	11.2	0.68	0.49
161	33.9	34.1	37.4	28.5	9.3	0.71	0.51
181	31.0	30.8	29.2	40.0	7.6	0.76	0.55
211	43.4	43.3	48.9	7.8	14.0	0.64	0.46
261	34.5	34.4	34.6	31.0	9.2	0.73	0.52
431	34.8	38.1	41.1	20.8	9.1	0.69	0.49
461	32.1	36.3	38.7	25.0	7.0	0.70	0.50

T_V Visible light transmission

R_s Solar reflectance

T_{UV} UV transmission

g_{tot} Total g-value

T_s Solar transmission

A_s Solar absorbance

F_C Shading factor

$F_C + g_{tot}$: Værdi beregnet med glas: 0.72 / $U_g = 1.6 \text{ W/m}^2 \text{ K}$, DIN EN 13363-1

Colorama Acoustic Multicolour




111



131



161



181



211



261



431



461

De viste farver er ikke bindende