

OSCURANTE

- Smooth dimout fabric with a pleasing haptic and colour matched reverse for a uniform appearance inside and out
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 72°
- Proven acoustic properties

ANVENDELSER



ANGIVELSER OM VÆVNING

	Semimørklægning
	Polyester
	250 g/m ²
	0.45 mm
	295 cm
	300 cm

VASKEANVISNINGER

						
-1%	-1.5%	-1.5%		-0.5%		

TEKNISKE EGENSKABER

	5-6
	Alpha-w = 0.60
	Flammehæmmende
	Kan anvendes i fugtige områder
	Egnet til Wave
	Oeko-Tex
	Særlige farver fra 200 m

FLAMMEHÆMMENDE

Class 1 (EN 13773)
Class 1 (UNI 8456)
Type B (BS 5867-2)



Oscurante

OPTISKE KOEFFICIENTER OG SOLKOEFFICIENTER ($\pm 5\%$, DIN EN 410)

Farve	T_v	T_s	R_s	A_s	F_c	g_{tot}
328	0.2	0.3	56.8	42.9	0.56	0.40
331	0.0	0.2	45.4	54.4	0.63	0.45
334	0.1	0.2	54.1	45.7	0.57	0.41
337	0.0	0.3	31.5	68.2	0.72	0.52
338	0.0	0.2	28.1	71.7	0.74	0.53
339	0.0	0.2	33.1	66.7	0.71	0.51
340	0.0	0.2	40.5	59.3	0.61	0.48
343	0.0	0.2	32.3	67.5	0.71	0.51
344	0.0	0.2	31.6	68.2	0.72	0.52
752	0.0	0.2	41.9	57.9	0.65	0.47
756	0.0	0.2	47.7	52.1	0.62	0.44
757	0.0	0.2	37.4	62.4	0.68	0.49

T_v Visible light transmission

R_s Solar reflectance

F_c Shading factor

T_s Solar transmission

A_s Solar absorption

g_{tot} Total g-value

$F_c + g_{tot}$: Værdi beregnet med glas: 0.72 / $U_g = 1.6 \text{ W/m}^2 \text{ K}$, DIN EN 13363-1

Oscurante

328




331



334



337



338



339



340



343



344



752



756



757

De viste farver er ikke bindende