

POLYFLAX

- Structured polyester fabric with a distinctively natural linen-look
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 72°

ANVENDELSER



ANGIVELSER OM VÆVNING

	Transparent
	Polyester
	100 g/m ²
	0.47 mm
	325 cm
	330 cm

VASKEANVISNINGER



TEKNISKE EGENSKABER

	5
	Flammehæmmende
	Kan anvendes i fugtige områder
	Egnet til Wave
	Oeko-Tex
	Særlige farver fra 120 m

FLAMMEHÆMMENDE

Class 1 (EN 13773)
Class 1 (UNI 8456)
Type B (BS 5867-2)



Polyflax

OPTISKE KOEFFICIENTER OG SOLKOEFFICIENTER ($\pm 5\%$, DIN EN 410)

Farve	T_V	T_S	R_S	A_S	T_{UV}	F_C	g_{tot}
100	59.9	58.7	37.4	3.9	34.9	0.73	0.52
120	54.2	56.0	36.5	7.5	46.9	0.73	0.53
160	39.7	48.8	30.5	20.7	38.6	0.76	0.55
220	53.1	56.0	35.9	8.1	48.0	0.73	0.53
240	44.7	51.5	33.5	15.0	43.4	0.75	0.54
740	35.2	47.5	25.8	26.7	39.1	0.79	0.57
760	31.8	46.1	24.9	29.0	37.9	0.80	0.57
940	28.7	39.3	30.9	29.8	26.3	0.75	0.54

T_V Visible light transmission

R_S Solar reflectance

T_{UV} UV transmission

g_{tot} Total g-value


T_S Solar transmission

A_S Solar absorption


F_C Shading factor

$F_C + g_{tot}$: Værdi beregnet med glas: $0.72 / U_g = 1.6 \text{ W/m}^2 \text{ K}$, DIN EN 13363-1


Polyflax




100




120




160




220




240



740



760



940

De viste farver er ikke bindende