

COLORAMA 2 MULTICOLOUR

- Exclusive Colorama Trevira CS fabric woven with a multicolour yarn for texture and tonality
- Cradle to Cradle Certified™ Bronze
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 72°
- Proven acoustic properties

APPLICATIONS



FABRIC PROPERTIES

	Semi transparent
	Polyester Trevira CS
	260 g/m ²
	0.55 mm
	325 cm
	330 cm
	330 cm

WASHING INSTRUCTIONS

	 -1%	 -2%	 -2.5%		 -0.5%		
	 -1%						
							

FEATURES / TECHNICAL PROPERTIES

	6
	Alpha-w = 0.30 / 0.65
	Flame retardant
	Applicable in humid areas
	Fabric must be turned
	Fabric must be turned
	Oeko-Tex, Cradle to Cradle

FIRE PROTECTION

B-s1,d0 (EN 13501-1)
 Class 1 (EN 13773)
 Class 1 (UNI 8456)
 B1 (DIN 4102-1)
 M1 (NF P 92-503/5/7)
 Type C (BS 5867-2)
 NFPA 701



Colorama 2 Multicolour

OPTICAL AND SOLAR COEFFICIENTS ($\pm 5\%$, DIN EN 410)

Colour	T_V	T_S	R_S	A_S	T_{UV}	F_C	g_{tot}
111	27.4	27.0	64.4	8.6	6.6	0.53	0.38
131	17.8	18.9	47.6	33.5	6.8	0.63	0.45
161	12.6	13.3	39.1	47.6	5.1	0.68	0.49
181	8.4	8.7	27.8	63.5	4.0	0.75	0.54
211	24.9	26.4	59.4	14.2	8.0	0.56	0.40
261	12.6	13.1	37.9	49.0	5.1	0.69	0.49
431	12.3	18.2	46.3	35.5	5.0	0.64	0.46
461	9.8	17.3	43.8	38.9	4.8	0.65	0.47

T_V Visible light transmission

R_S Solar reflectance

T_{UV} UV transmission

g_{tot} Total g-value


T_S Solar transmission

A_S Solar absorption

F_C Shading factor

$F_C + g_{tot}$: Value calculated with glass: $0.72 / U_g = 1.6 \text{ W/m}^2 \text{ K}$, DIN EN 13363-1

Colorama 2 Multicolour




111



131



161



181



211



261



431



461

Colours shown are not binding