

## LEVISO LIGHT

- Subtly textured dimout fabric with a soft finished form
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 60°
- Proven acoustic properties

### APPLICATIONS



### FABRIC PROPERTIES

|                                                                                     |                      |
|-------------------------------------------------------------------------------------|----------------------|
|    | Dimout               |
|    | Polyester            |
|  | 300 g/m <sup>2</sup> |
|  | 0.62 mm              |
|   | 295 cm               |
|   | 300 cm               |

### WASHING INSTRUCTIONS



### FEATURES / TECHNICAL PROPERTIES

|                                                                                     |                            |
|-------------------------------------------------------------------------------------|----------------------------|
|    | 4-5                        |
|    | Alpha-w = 0.80             |
|  | Flame retardant            |
|  | Fabric must be turned      |
|  | Fabric must be turned      |
|  | Oeko-Tex                   |
|  | Special colours from 400 m |

### FIRE PROTECTION

Class 1 (EN 13773)  
M1 (NF P 92-503/5/7)  
Type B (BS 5867-2)



## Leviso Light

### OPTICAL AND SOLAR COEFFICIENTS ( $\pm 5\%$ , DIN EN 410)

| Colour | $T_V$ | $T_S$ | $R_S$ | $A_S$ | $F_C$ | $g_{tot}$ |
|--------|-------|-------|-------|-------|-------|-----------|
| 1      | 0.6   | 1.0   | 59.8  | 39.2  | 0.54  | 0.39      |
| 2      | 0.6   | 1.0   | 59.8  | 39.2  | 0.54  | 0.39      |
| 3      | 0.6   | 1.0   | 59.8  | 39.2  | 0.54  | 0.39      |
| 8      | 0.6   | 1.0   | 59.8  | 39.2  | 0.54  | 0.39      |
| 9      | 0.0   | 0.8   | 44.5  | 54.7  | 0.64  | 0.46      |
| 11     | 0.0   | 0.8   | 44.5  | 54.7  | 0.64  | 0.46      |
| 12     | 0.0   | 0.8   | 44.5  | 54.7  | 0.64  | 0.46      |
| 14     | 0.0   | 0.9   | 37.1  | 62.0  | 0.68  | 0.49      |
| 17     | 0.0   | 0.8   | 44.5  | 54.7  | 0.64  | 0.46      |
| 18     | 0.0   | 0.9   | 37.1  | 62.0  | 0.68  | 0.49      |
| 19     | 0.0   | 0.9   | 37.1  | 62.0  | 0.68  | 0.49      |
| 23     | 0.0   | 0.9   | 37.1  | 62.0  | 0.68  | 0.49      |
| 25     | 0.0   | 0.9   | 37.1  | 62.0  | 0.68  | 0.49      |
| 27     | 0.6   | 1.0   | 59.8  | 39.2  | 0.54  | 0.39      |
| 28     | 0.0   | 0.9   | 37.1  | 62.0  | 0.68  | 0.49      |
| 29     | 0.0   | 0.9   | 34.0  | 65.1  | 0.70  | 0.51      |
| 30     | 0.0   | 0.9   | 34.0  | 65.1  | 0.70  | 0.51      |
| 31     | 0.0   | 0.9   | 37.1  | 62.0  | 0.68  | 0.49      |
| 32     | 0.0   | 0.8   | 44.5  | 54.7  | 0.64  | 0.46      |
| 33     | 0.6   | 1.0   | 59.8  | 39.2  | 0.54  | 0.39      |

$T_V$  Visible light transmission

$R_S$  Solar reflectance


$F_C$  Shading factor

$T_S$  Solar transmission

$A_S$  Solar absorption

$g_{tot}$  Total g-value

Fc + gtot: Value calculated with glass: 0.72 / Ug = 1.6 W/m<sup>2</sup> K, DIN EN 13363-1

**Leviso Light**


1



2



3




8



9




11



12




14



17



18



19



23



25



27




28




29



30



31



32



33

Colours shown are not binding